

**RUST-OLEUM®****6200 SYSTEM****FAST-CURE EPOXY FLOOR COATING****DESCRIPTION AND USES**

The 6200 System Fast-Cure Epoxy Floor Coating is a two component, epoxy coating designed for use on concrete floors in mild to moderate industrial environments. It is suitable for areas with heavy foot traffic, fork lift traffic and mild chemical spills.

This solvent-based coating offers easy application by roller and brush; dries quickly and requires only minimal surface preparation.

This product complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

**PRODUCTS**

Component	Description
251768	Dunes Tan Base Component
251767	Silver Gray Base Component
251770	Activator

**APPEARANCE**

Semi-gloss

**PACKAGING**

The 6200 System is packaged in a one gallon kit. Each kit contains the base component and activator.

SKU	Description
251765	Dunes /Tan Kit
251763	Silver Gray Kit

**PRODUCT APPLICATION****SURFACE PREPARATION**

New concrete should be allowed to cure for 30 days before application of any coating. If there is any doubt about the dryness of the concrete, conduct a test by simply taping a piece of 4 mil plastic sheet 18x18" on the bare concrete for 24 hours. Be sure to tape all four sides. After 24 hours, check the concrete for signs of moisture. The concrete substrate will be darker if damp. If moisture is found, allow additional drying time (10-14 days) and repeat the test. If repeated tests continue to indicate the presence of moisture, contact Rust-Oleum Technical Service for assistance.

Check for curing compounds or other types of sealers by pouring a small amount of water onto the concrete. If water soaks in, the surface is porous enough for coating. If water soaks in, the surface is suitable for coating. If water beads up on the concrete, the surface is not porous and a test application is warranted to ensure proper adhesion will develop. Sanding or mechanical abrading may be required if proper adhesion does not develop. Contact Rust-Oleum Technical Service for detailed information.

Remove oil, dirt and other chemical contaminants by cleaning with Industrial Pure Strength 3599 Cleaner/Degreaser, detergent or other suitable cleaner and rinse with fresh water. This is best accomplished using a standard scrubber or polisher with a heavy duty stripping pad (such as 3M 7300 or similar).

**PRODUCT APPLICATION (cont.)**

For optimal performance, acid etch or shot blast the concrete to remove laitance and create a surface profile. Acid etch can be done if the concrete is free of curing agents or sealers. Etch the concrete with 108 Clean & Etch Solution. Rinse thoroughly and immediately and allow to dry. After completion, the concrete should have a texture, which resembles fine grit sandpaper. Repeat the process if necessary. Consult with 108 Clean & Etch Solution Technical Data Sheet, Form 1069990, for complete application instructions. The floor should be dry and dust free prior to application. Vacuum to remove fine dust and debris.

Previously coated floors need to be in good condition with proper adhesion to the concrete substrate. Check the adhesion of the previous coating by cutting a small X in the coating using a sharp razor knife. Firmly apply a piece of 2" duct tape over the center of the X cut, and then pull off with a fast snap. The coating is suitable to topcoat if no significant previous coating is removed beyond the X cut. If the coating fails this test, then additional surface preparation is required.

**MIXING**

Both the base and activator components are highly pigmented. Mix each component thoroughly to ensure any settle pigment is re-dispersed before combining the components together. Once combined, mix thoroughly for 2-3 minutes. Power mixing is preferred. Do not mix more material than you plan to use with the listed pot life.

**APPLICATION**

Apply only when air and surface temperatures are between 50-100°F (10-38°C) and surface is at least 5°F above the dew point and the relative humidity is below 85% during and after application. Apply by roller using a good quality (shed resistant) 3/8" synthetic nap cover. Avoid applying excessive material. Do not allow the coating to puddle. The coating should be applied within the published coverage rate of 175-350 square feet per gallon. The coverage rate will vary depending on the porosity and surface texture of the concrete. On new or uncoated concrete, two coats of product should be applied. Do not thin.

**DRY AND RECOAT TIMES**

The coated floor will be ready for foot traffic 5 hours after application of the final coat. The coating will be ready for full use in 48-72 hours at 70-80°F (21-27°C) and 50% relative humidity. Allow coated floor to cure for 5 days before mopping or washing. Use Rust-Oleum 200 Anti-skid Floor Coating additive for skid resistance where oil or water spillage is a problem.

**THINNING**

Do not thin this product.

**CLEAN-UP**

160 Thinner OR MEK.



## TECHNICAL DATA

# 6200 SYSTEM FAST-CURE EPOXY FLOOR COATING

### PHYSICAL PROPERTIES

		FAST-CURE EPOXY FLOOR COATING	
<b>Resin Type</b>		Amidoamine or Polyamine converted Epoxy	
<b>Pigment Type</b>		Varies with color	
<b>Solvents</b>		Aromatic Hydrocarbons, Ketones and Alcohols	
<b>Weight*</b>	<b>Per Gallon</b>	12.1-13.2 lbs.	
	<b>Per Liter</b>	1.4-1.5 kg	
<b>Solids*</b>	<b>By Weight</b>	81.3-83.5%	
	<b>By Volume</b>	68.3-69.8%	
<b>Volatile Organic Compounds*</b>		<250 g./l. (2.08 lbs./gal.)	
<b>Mixing Ratio</b>		1:1 base to activator by volume	
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		2.5-5.5 mils (62.5-137.5μ)	
<b>Wet Film to Achieve DFT (unthinned material)</b>		3.5-8.0 mils (87.5-200μ)	
<b>Theoretical Coverage at 1 mil DFT (25μ)</b>		1095-1120 sq.ft./gal. (26.9-27.6 m <sup>2</sup> /l)	
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		Smooth	300-350 sq.ft./gl. (7.4-8.6 m <sup>2</sup> /l)
		Medium	200-300 sq.ft./gal. (4.9-7.4 m <sup>2</sup> /l)
		Rough	175-200 sq.ft./gal. (4.3-4.9m <sup>2</sup> /l)
<b>Induction Period</b>		None required	
<b>Pot Life**</b>	<b>1-Gallon</b>	2-4 hours at 70°F (15°C)	1-2 hours at 90°F (32°C)
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Recoat</b>	4 hours	
	<b>Light Traffic</b>	5 hours	
	<b>Heavy Traffic</b>	48-72 hours	
<b>Dry Heat Resistance</b>		300°F (149°C). Color may shift above 150°F (66°C).	
<b>Shelf Life</b>		Base Component 3 years; Activator 2 years (unopened containers).	
<b>Safety Information</b>		For additional information, see SDS	

\* Activated material

\*\*Pot life is affected by air temperature, amount of material activated and quantity of thinner used. Avoid activating large quantities at temperatures above 80°F (27°C). At temperatures above 90°F (32°C), the pot life of unthinned material in 5-gallon pails may be very short (less than 1 hour).

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.